

N813 CLOUD REC



7219 nero



0614 amaranta



5710 white - 1210 white PFP



5316 new blu cina

N813 CLOUD REC

Applications

> Swimwear > Lining > Underwear

Ultra-light, buttery hand feeling fabric, made with 100% Recycled Nylon, can be used for sophisticated lining on a swimsuit and for intimate.



Composition

Recycled Polyamide		Elastane	
87%		13%	
Weight (+5%)		Width (+3%/-2%)	
140 g/m²	213 g/m lin.	150 cm	
Courses	Wales	Tolerance for composition (standard ASTM)	
38/cm	28/cm	±3%	
Dimensional Change of fabric after HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)		Max	Max
Resistance to pilling ASTM D 3512-Random tumble at 30 minutes photographic rating STD		-5%	-5%
Ultraviolet Protection Factor (U.P.F.) AATCC 183-2010		Width	Length
Stretch to dynamometer (+15%) ASTM D 4964 - LOAD 20 LBS		4 to 4.5	
Modulus % elongation (30% - 50% - 70%)		40/50+	
Care labelling codes		125%	130%
		Width	Length
		(min 106% - max 144%)	(min 110% - max 149%)
		30% 50% 70%	30% 50% 70%
		0.0-0.3 0.3-0.7 0.7-1.9	0.1-0.5 0.5-1.0 1.0-2.0
		Width Lbs	Length Lbs

AATCC Standards

COLOUR	CHLORINATED WATER AATCC 162	LIGHT AATCC 16-20 AFU	WATER 38°C AATCC 107							SEA WATER 38°C AATCC 106							PERSPIRATION AATCC 15							CROCKING AATCC 8		WASHING 49°C AATCC 61-2A						
	C.C.	C.C.	C.C.	AC	CO	PA	PL	PC	WO	C.C.	AC	CO	PA	PL	PC	WO	C.C.	AC	CO	PA	PL	PC	WO	S.CO DRY	S.CO WET	C.C.	AC	CO	PA	PL	PC	WO
	5710	3	3	4.5	5	5	5	5	5	5	4.5	5	5	5	5	5	5	4.5	5	5	5	5	5	5	5	5	4.5	5	5	5	5	5
1210	3	3	4.5	5	5	5	5	5	5	4.5	5	5	5	5	5	5	4.5	5	5	5	5	5	5	5	5	4.5	5	5	5	5	5	5
0614	4	4.5	4.5	4	3.5	3.5	4	4	3.5	4.5	4	3.5	3.5	4	3.5	3.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	3	4.5	4.5	4.5	3	4	4.5	4.5
5316	3	3.5	4.5	3.5	3	2.5	3	3	2.5	4.5	4	3	2.5	3	3	2.5	4.5	4.5	4	3.5	4.5	4.5	3.5	4.5	3.5	4	4.5	3.5	3	4.5	4.5	3.5
7219	4.5	4.5	4.5	4	4	3.5	3.5	4	3.5	4.5	4.5	4	3.5	4	4.5	4	4.5	4.5	4.5	4	4.5	4.5	4.5	4.5	3	4.5	4.5	4	3.5	4	4.5	4

ISO Standards

COLOUR	CHLORINATED WATER ISO 105-E03	LIGHT ISO 105-B02	WATER ISO 105-E01			SEA WATER ISO 105-E02			ALKALINE PERSPIRATION PH 8.0 ISO 105-E04			ACID PERSPIRATION PH 5.5 ISO 105-E04			CROCKING ISO 105-X12		WASHING 40°C ISO 105-C06 A2S		
	C.C.	C.C.	C.C.	CO	PA	C.C.	CO	PA	C.C.	CO	PA	C.C.	CO	PA	S.CO DRY	S.CO WET	C.C.	CO	PA
	5710	2-3	3	4-5	5	5	4-5	5	5	4-5	5	5	4-5	5	5	5	5	4-5	5
1210	2-3	3	4-5	5	5	4-5	5	5	4-5	5	5	4-5	5	5	5	5	4-5	5	5
0614	3-4	4-5	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	3	4-5	4-5	3-4
5316	2-3	3-4	4-5	4	3-4	4-5	4	3-4	4-5	3-4	3	4-5	4	3	4-5	3-4	4-5	3-4	3-4
7219	4-5	4-5	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	3	4-5	4-5	3-4

Available colors: the 4 colors presented in this page are always available for sampling. If you would like to choose a color from the main Polyamide color card, you can enjoy a MCQ of only 70 mts for bulk orders. However, the resulting color shade and the color fastness performance may be slightly different. We will submit to your attention a lab dip swatch for approval before going on with the bulk production.

Special notes/warnings: we recommend carrying out lab tests for color matches, molding, bonding and applications on fabrics in order to prevent problems from arising during garments production. Please carefully check physical data and color fastness forecasts.



N813 **CLOUD REC**



UV
protection



two way
stretch



comfort
fit



soft
touch