

N110 KIRA

SWIMWEAR CREORA
Highclo



HUNG YEN'S SIGNATURE MATTE CHARMEUSE! HIGH PERFORMANCE VERSATILITY, N110 KIRA IS THE BEST CHOICE FOR ANY ESSENTIAL WATER GARMENT COLLECTION.



HIGH CHLORINE RESISTANCE



UV PROTECTION



FOUR WAY STRETCH



COMFORT FIT



DIGITAL PRINTING



CONSCIOUSLY MANUFACTURED

COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3% / -2% TOLERANCE)	COURSES	WALES							
80% POLYAMIDE	20% ELASTANE HIGH-CHLORINE RESISTANCE	195 G/M ²	150 CM	49 / CM	27 / CM							
		5.8 OZ/YD ²	59 INCHES	124 / INCHES	66 / INCHES							
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 WASH, NORMAL CYCLE AT 41 DEGREE CELSIUS LINE DRY)		RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD		ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183-2010								
MAX -5% WIDTH	MAX -5% LENGHT	4.0 TO 4.5		40 TO 50+								
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 LBS	SOLID						PFP					
	110% WIDTH (MIN 94% - MAX 127%)			215% LENGTH (MIN 183% - MAX 247%)			110% WIDTH (MIN 94% - MAX 127%)			205% LENGTH (MIN 175% - MAX 236%)		
MODULUS @ % ELONGATION (30% - 50% - 70%)	30%	50%	70%	30%	50%	70%	30%	50%	70%	30%	50%	70%
	0.3 - 1.0	1.0 - 2.0	2.2 - 4.0	0.0 - 0.2	0.3 - 1.0	1.0 - 1.6	0.3 - 1.0	1.0 - 1.8	1.8 - 3.8	0.0 - 0.3	0.3 - 1.0	1.0 - 1.8
CARE LABELLING SYMBOLS												

AVAILABLE COLORS THE CHOICE OF COLORS FOR VIRGIN POLYAMIDE FABRICS REFERS TO THE MAIN POLYAMIDE COLOR CARD, YOU CAN ENJOY A MCQ OF 70 MTS FOR BULK ORDERS. HOWEVER, THE RESULTING COLOR SHADE AND THE COLOR FASTNESS PERFORMANCES MAY BE SLIGHTLY DIFFERENT. WE WILL SUBMIT TO YOUR ATTENTION A LAB DIP SWATCH FOR APPROVAL BEFORE GOING ON WITH THE BULK PRODUCTION.

SPECIAL NOTES/WARNINGS WE RECOMMEND CARRYING OUT LAB TESTS FOR COLOR MATCHES, MOLDING, BONDING AND APPLICATIONS ON FABRICS IN ORDER TO PREVENT PROBLEMS FROM ARISING DURING GARMENTS PRODUCTION. PLEASE CAREFULLY CHECK PHYSICAL DATA AND COLOR FASTNESS FORECASTS.