RECYCLED SHINY POLYAMIDE

N232 SIRIUS REC

COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3% / -2% TOLERANCE)	COURSES	WALES
80% TRILOBAL RECYCLED SHINY POLYAMIDE	20% ELASTANE HIGH-CHLORINE RESISTANCE	175 G/M^2	150 CM	44 / CM	25 / CM
		5.2 OZ/YD^2	59 INCHES	112 / INCHES	64 / INCHES

DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 WASH, NORMAL CYCLE AT 41 DEGREE CELSIUS LINE DRY)		RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183-2010
MAX -5% WIDTH	MAX -5% LENGHT	4.0 TO 4.5	40 TO 50+

STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 LBS	SOLID						PFP					
	110% WIDTH (MIN 94% - MAX 127%)			175% LENGTH (MIN 149% - MAX 201%)			110% WIDTH (MIN 94% - MAX 127%)			165% LENGTH (MIN 140% - MAX 201%)		
MODULUS @ % ELONGATION (30% - 50% - 70%)	30%	50%	70%	30%	50%	70%	30%	50%	70%	30%	50%	70%
	0.2 - 0.8	0.8 - 1.4	1.4 - 3.2	0.0 - 0.3	0.4 - 1.1	1.1 - 1.9	0.3 - 0.9	1.0 - 1.8	2.1 - 3.9	0.0 - 0.3	0.4 - 1.2	1.3 - 2.1
CARE LABELLING SYMBOLS												


2518 CHAMPAGNE


9917 DARK OLIVE


2319 BLACK


1410 WHITE / 1910 PFP

AATCC STANDARDS

COLOUR	CHLORINATED WATER AATCC 162	LIGHT AATCC 16-20 AFU	WATER 38°C AATCC 107							SEA WATER 38°C AATCC 106							PERSPIRATION AATCC 15							CROCKING AATCC 8		WASHING 49°C AATCC 61-2A						
	C.C.	C.C.	C.C.	AC	CO	PA	PL	PC	WO	C.C.	AC	CO	PA	PL	PC	WO	C.C.	AC	CO	PA	PL	PC	WO	S.CO DRY	S.CO WET	C.C.	AC	CO	PA	PL	PC	WO
1410 / 1910	3	3	4.5	5	5	5	5	5	5	4.5	5	5	5	5	5	5	4.5	5	5	5	5	5	5	5	5	4.5	5	5	5	5	5	5
9917	4	4	4.5	4	4	3.5	4	4	4	4.5	4	4	4	4.5	4.5	4	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	3.5	4.5	4.5	4.5	3.5	4.5	4.5	4
2518	4	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4.5
2319	4.5	4.5	4.5	4	4.5	3.5	4.5	4.5	3.5	4.5	4.5	4.5	3.5	4.5	4.5	3.5	4.5	4.5	4.5	4	4.5	4.5	4	4	3	4.5	4.5	4.5	3.5	4.5	4.5	4

ISO STANDARDS

COLOUR	CHLORINATED WATER ISO 105-E03	LIGHT ISO 105-B02	WATER ISO 105-E01				SEA WATER ISO 105-E02				ALKALINE PERSPIRATION PH 8.0 ISO 105-E04				ACID PERSPIRATION PH 5.5 ISO 105-E04				CROCKING ISO 105-X12		WASHING 40°C ISO 105-C06 A2S			
	C.C. 50 MG/L	C.C.	C.C.	CO	PA	PL	C.C.	CO	PA	PL	C.C.	CO	PA	PL	C.C.	CO	PA	PL	S.CO DRY	S.CO WET	C.C.	CO	PA	PL
1410 / 1910	2-3	3	4-5	5	5	5	4-5	5	5	5	4-5	5	5	5	4-5	5	5	5	5	5	4-5	5	5	5
9917	3-4	4	4-5	4-5	4	4-5	4-5	4-5	4	4-5	4-5	4-5	4	4-5	4-5	4-5	4	4-5	4-5	3-4	4-5	4-5	4	4-5
2518	3	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
2319	4	4-5	4-5	4-5	4	4-5	4-5	4-5	4	4-5	4-5	4-5	4	4-5	4-5	4-5	4	4-5	4	3	4-5	4-5	4	4-5

ALL COLORS DISPLAYED IN THE MAIN SHINY COLOR CARD ARE AVAILABLE FOR SAMPLING ON THIS ITEM. PLEASE REFER TO THE MAIN SHINY COLOR CARD FOR THE COLOR FASTNESS PERFORMANCES OF EACH COLOR. YOU CAN PLACE BULK ORDERS WITH MCQ 70 MTS IN ANY SHADE OF OUR COLLECTION. HOWEVER, THE RESULTING COLOR SHADE AND THE COLOR FASTNESS PERFORMANCES MAY BE SLIGHTLY DIFFERENT. WE WILL SUBMIT TO YOUR ATTENTION A LAB DIP SWATCH FOR APPROVAL BEFORE GOING ON WITH THE BULK PRODUCTION.

SPECIAL NOTES/WARNINGS WE RECOMMEND CARRYING OUT LAB TESTS FOR COLOR MATCHES, MOLDING, BONDING AND APPLICATIONS ON FABRICS IN ORDER TO PREVENT PROBLEMS FROM ARISING DURING GARMENTS PRODUCTION. PLEASE CAREFULLY CHECK PHYSICAL DATA AND COLOR FASTNESS FORECASTS.

SWIMWEAR
UNDERWEAR

THE LIGHT SIDE OF THE GLAMOROUS SHINY COLLECTION NOW AVAILABLE IN ITS RECYCLED VERSION. PRESERVED LIGHT WEIGHT FOR VIRTUOUS APPLICATIONS, WHICH GRANTS AT THE SAME TIME, GOOD ELASTIC PERFORMANCES AND COMFORT. UNCHANGED SPARKLING BRIGHTNESS OF ALL COLORS AND COLOR FASTNESS PROPERTIES. ANOTHER BRAND NEW MEMBER OF THE SHINIEST - NOW SUSTAINABLE – COLLECTION, IDEAL FOR DANCEWEAR, FASHION UNDERWEAR AND SWIMWEAR.

SHINY
HIGH CHLORINE RESISTANCE
UV PROTECTION
FOUR WAY STRETCH
FOUR WAY STRETCH
COMFORT FIT
DIGITAL PRINTING
CONSCIOUSLY MANUFACTURED

Global Recycled Standard ©TextileExchange
CU1004128

CREORA Highclo