

CREORĀ *SWIMWEAR*
Highclo

N320 MAMI

SHAPEWEAR-LIKE FABRIC THAT ENSURES HIGH-COVERAGE PERFORMANCES FOR SWIMWEAR AND BEACHWEAR GARMENTS, WHILE MAINTAINING A NATURAL CONTROL OF THE BODY CURVES.



HIGH CHLORINE RESISTANCE



UV PROTECTION



SHAPE RETENTION



FOUR WAY STRETCH



COMFORT FIT



DIGITAL PRINTING



CONSCIOUSLY MANUFACTURED



COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3% / -2% TOLERANCE)	COURSES	WALES								
77% POLYAMIDE	23% ELASTANE HIGH-CHLORINE RESISTANCE	215 G/M ²	150 CM	46 / CM	26 / CM								
		6.3 OZ/YD ²	59 INCHES	117 / INCHES	66 / INCHES								
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 WASH, NORMAL CYCLE AT 41 DEGREE CELSIUS LINE DRY)		RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD		ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183-2010									
MAX -5% WIDTH	MAX -5% LENGHT	4.5		50+									
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 LBS		SOLID						PFP					
		100% WIDTH (MIN 85% - MAX 115%)			170% LENGTH (MIN 145% - MAX 196%)			95% WIDTH (MIN 81% - MAX 110%)			170% LENGTH (MIN 145% - MAX 196%)		
MODULUS @ % ELONGATION (30% - 50% - 70%)		30%	50%	70%	30%	50%	70%	30%	50%	70%	30%	50%	70%
		0.4-0.9	0.9-2.0	2.0-4.0	0.2-0.8	0.8-1.6	1.6-2.6	0.6-1.2	1.6-2.8	3.4-6.6	0.0-0.6	0.8-1.5	1.5-2.5
CARE LABELLING SYMBOLS													

AVAILABLE COLORS THE CHOICE OF COLORS FOR VIRGIN POLYAMIDE FABRICS REFERS TO THE MAIN POLYAMIDE COLOR CARD, YOU CAN ENJOY A MCQ OF 70 MTS FOR BULK ORDERS. HOWEVER, THE RESULTING COLOR SHADE AND THE COLOR FASTNESS PERFORMANCES MAY BE SLIGHTLY DIFFERENT. WE WILL SUBMIT TO YOUR ATTENTION A LAB DIP SWATCH FOR APPROVAL BEFORE GOING ON WITH THE BULK PRODUCTION.

SPECIAL NOTES/WARNINGS WE RECOMMEND CARRYING OUT LAB TESTS FOR COLOR MATCHES, MOLDING, BONDING AND APPLICATIONS ON FABRICS IN ORDER TO PREVENT PROBLEMS FROM ARISING DURING GARMENTS PRODUCTION. PLEASE CAREFULLY CHECK PHYSICAL DATA AND COLOR FASTNESS FORECASTS.