

TECHNICAL DATA SHEET

26/02/2022

N813

CLOUD REC SOLID

COMPOSITION

87%
PA REC

RECYCLED
NYLON

13%
EA

ELASTANE
High Chlorine
resistance


OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
21CX00135 CENTROCOT
Tested for harmful substances.
www.oeko-tex.com/standard100

WORK IN ECO

Global Recycled Standard

Creora
HighTetra

WEIGHT (±5%)	WIDTH (+3%/-2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)	
140 g/m ²	213 g/m lin.	150 cm	38/cm	28/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL <small>AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)</small>	max -5% WIDTH	max -5% LENGTH
RESISTANCE TO PILLING <small>ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD</small>	4 to 4.5	
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) <small>AATCC 183-2010</small>	40/50+	
STRETCH TO DYNAMOMETER (±15%) <small>ASTM D4964 - LOAD 20 Lbs</small>	125% WIDTH <small>(min 106% - max 144%)</small>	130% LENGTH <small>(min 110% - max 149%)</small>
MODULUS @ % ELONGATION (30% - 50% - 70%)	30% 50% 70%	30% 50% 70%
	0.0 - 0.3 0.3 - 0.7 0.7 - 1.9	0.1 - 0.5 0.5 - 1.0 1.0 - 2.0
CARE LABELLING CODES		

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.

TECHNICAL DATA SHEET PROVISIONAL


26/01/2022

N813

CLOUD REC


PFP

COMPOSITION







87%
PA REC

RECYCLED
NYLON








13%
EA

ELASTANE
High Chlorine
resistance

WEIGHT (±5%)		WIDTH (+3%/-2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
140 g/m ²	213 g/m lin.	150 cm	38/cm	28/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	max -5% WIDTH			max -5% LENGTH		
	4 to 4.5					
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	40/50+					
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) AATCC 183-2010	40/50+					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs	115% WIDTH (min 98% - max 132%)			130% LENGTH (min 110% - max 149%)		
	30%	50%	70%	30%	50%	70%
MODULUS @ % ELONGATION (30% - 50% - 70%)	0.0 - 0.4	0.4 - 1.2	1.2 - 2.4	0.1 - 0.6	0.6 - 1.2	1.2 - 2.2
	WIDTH Lbs			WIDTH Lbs		
CARE LABELLING CODES	    					

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.