

N880 HAWAII SOLID

PROVISIONAL TECHNICAL DATASHEET November 2025



COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES
76% RECYCLED NYLON	24% ELASTANE HIGH-CHLORINE RESISTANCE	165 g/m ²	145 cm	52 / cm	29 / cm
		4.86 oz/yd ²	57 inch	132 / inch	74 / inch
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41 degree Celsius, tumble dry low)			max -4% WIDTH		max -4% LENGTH
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			4.0 to 4.5		
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			50+		
SOLID					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs			155% WIDTH (min 132% - max 178%)		110% LENGTH (min 94% - max 127%)
MODULUS @ % ELONGATION (30%-50%-70%)			30%	50%	70%
			0.2-0.6	0.6-1.2	1.2-2.0
			WIDTH Lbs		
CARE LABELLING CODES					

CERTIFICATIONS



FUNCTIONAL YARNS

SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.