

# TECHNICAL DATA SHEET

29/08/2022

## P740 FOX REC SOLID






### COMPOSITION

**84%**  
PL REC


TEXTURIZED  
RECYCLED  
POLYESTER

**16%**  
EA

ELASTANE  
High Chlorine  
resistance

WEIGHT (±5%)	329 g/m lin.	WIDTH (+3%/-2%)	153 cm	COURSES	44/cm	WALES	26/cm	TOLERANCE FOR COMPOSITION (STANDARD ASTM)	±3%
215 g/m <sup>2</sup>	329 g/m lin.	153 cm	44/cm	26/cm	±3%				

<b>DIMENSIONAL CHANGE OF FABRIC AFTER HL</b> <small>AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)</small>	<b>max -5%</b> WIDTH	<b>max -5%</b> LENGTH
<b>RESISTANCE TO PILLING</b> <small>ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD</small>	<b>4 to 4.5</b>	
<b>ULTRAVIOLET PROTECTION FACTOR (U.P. F.)</b> <small>AATCC 183-2010</small>	<b>50+</b>	
<b>STRETCH TO DYNAMOMETER (±15%)</b> <small>ASTM D4964 - LOAD 20 Lbs</small>	<b>125%</b> WIDTH <small>(min 106% - max 144%)</small>	<b>180%</b> LENGTH <small>(min 153% - max 207%)</small>
<b>MODULUS @ % ELONGATION (30% - 50% - 70%)</b>	30%    50%    70%	30%    50%    70%
	<b>0.1 - 0.7    0.7 - 1.6    1.3 - 3.8</b>	<b>0.0 - 0.4    0.6 - 1.4    1.4 - 2.2</b>
<b>CARE LABELLING CODES</b>		

### SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.