




P375 SPRINT REC

COMPOSITION <small>(ASTM Standard ±3% tolerance)</small>		WEIGHT <small>(±5% TOLERANCE)</small>	WIDTH <small>(+3% / -2% TOLERANCE)</small>	COURSES	WALES			
53% RECYCLED POLYESTER	47% POLYESTER PBT	175 g/m ²	160 cm	26 / cm	21 / cm			
		5.2 oz/yd ²	63 inches	66 / inches	53 / inches			
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 WASH, NORMAL CYCLE AT 41 DEGREE CELSIUS LINE DRY)		RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD		ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183-2010				
max -5% WIDTH	max -5% LENGHT	4.5		40 to 50+				
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs			SOLID					
			115% WIDTH <small>(min 98% - max 132%)</small>			75% LENGTH <small>(min 64% - max 86%)</small>		
MODULUS @ % ELONGATION (30% - 50% - 70%)			30%	50%	70%	30%	50%	70%
			0.1 - 0.5	0.6 - 1.3	1.5 - 2.7	0.7 - 1.7	2.8 - 5.2	9.5 - 18.5
CARE LABELLING CODES								



*2413 neon pink



10717 deep teal



9919 black



07110 white / PFP

AATCC Standards

COLOUR	CHLORINATED WATER AATCC 162	LIGHT AATCC 16-20 AFU	WATER 38°C AATCC 107							SEA WATER 38°C AATCC 106							PERSPIRATION AATCC 15							CROCKING AATCC 8		WASHING 49°C AATCC 61-2A							
	C.C.	C.C.	C.C.	AC	CO	PA	PL	PC	WO	C.C.	AC	CO	PA	PL	PC	WO	C.C.	AC	CO	PA	PL	PC	WO	S.CO DRY	S.CO WET	C.C.	AC	CO	PA	PL	PC	WO	
	07110	4.5	4.5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5
*2413	4.5	3.5	4.5	4	4.5	3.5	4.5	4.5	3.5	4.5	4	4.5	3.5	4.5	4.5	3.5	4.5	4.5	4.5	4	4.5	4.5	4	4	4.5	4.5	4	4	3	4	4.5	5	
10717	4.5	3.5	4.5	4	4.5	4	4.5	4.5	4	4.5	4	4.5	4	4.5	4.5	4	4.5	4.5	4.5	4.5	4.5	4.5	4.5	4	4	4.5	4	4.5	3.5	4	4.5	4.5	
9919	4.5	4.5	4.5	4	4.5	3.5	4	4.5	3.5	4.5	4	4.5	3.5	4	4.5	3.5	4.5	4.5	4.5	4	4.5	4.5	4.5	4	4	4.5	4	4.5	3.5	4	4.5	4	

* Fluorescent Colours ¹ Fluorescent Colours - CF TO LIGHT AATCC 16-10 AFU

ISO Standards

COLOUR	CHLORINATED WATER ISO 105-E03	LIGHT ISO 105-B02	WATER ISO 105-E01			SEA WATER ISO 105-E02			ALKALINE PERSPIRATION PH 8.0 ISO 105-E04			ACID PERSPIRATION PH 5.5 ISO 105-E04			CROCKING ISO 105-X12		WASHING 40°C ISO 105-C06 A2S		
	C.C. 50 mg/l	C.C.	C.C.	CO	PA	C.C.	CO	PA	C.C.	CO	PA	C.C.	CO	PA	S.CO DRY	S.CO WET	C.C.	CO	PA
	07110	4-5	4-5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5
*2413	4	3	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4	4-5	4-5	4-5	4
10717	4	3-4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4	4	4-5	4-5	4
9919	4-5	4-5	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4	4	4-5	4-5	4

Available colors the 4 colors presented in this page are always available for sampling. If you would like to choose a color from the main **Polyester color card**, you can enjoy a MCQ of only 70 mts for bulk orders. However, the resulting color shade and the color fastness performance may be slightly different. We will submit to your attention a lab dip swatch for approval before going on with the bulk production.

Special notes/warnings we recommend carrying out lab tests for color matches, molding, bonding and applications on fabrics in order to prevent problems from arising during garments production. Please carefully check physical data and color fastness forecasts.

P375 SPRINT REC

SWIMWEAR

SPORTSWEAR

The soft-texturized 100% Polyester Recycled and PBT solution for performance swimwear and sportswear. Comfortable, light fitting, high coverage and chlorine-proof - thanks to its composition - this fabric is suitable for competition and training water and dry activities.



CHLORINE
PROOF



UV
PROTECTION



TEXTURIZED
TOUCH



HIGH
COVERAGE



QUICK-DRY



FOUR WAY
STRETCH



COMFORT
FIT



SUBLIMATION
PRINT



CU1004128GRS-2023-00035481