

TECHNICAL DATA SHEET

04/05/2020

P515 YORI REC SOLID

COMPOSITION

82%
PL REC


RECYCLED
POLYESTER

18%
EA

ELASTANE
High Chlorine
resistance



WEIGHT (±5%)		WIDTH (+3%/-2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
195 g/m ²	293 g/m lin.	150 cm	44/cm	26/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	max -5% WIDTH			max -5% LENGTH		
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	4 to 4.5					
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) AATCC 183-2010	40/50+					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs	100% WIDTH (min 85% - max 115%)			140% LENGTH (min 119% - max 161%)		
MODULUS @ % ELONGATION (30% - 50% - 70%)	30%	50%	70%	30%	50%	70%
	0.2 - 1.0	1.1 - 2.6	3.0 - 7.2	0.0 - 0.8	0.9 - 1.6	1.7 - 3.1
	WIDTH Lbs			WIDTH Lbs		
CARE LABELLING CODES						

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.


To improve our products, we reserve the right to modify these when necessary.

TECHNICAL DATA SHEET

22/07/2020


P535 YETI REC PFP

COMPOSITION



78%
PL REC

RECYCLED
POLYESTER



22%
EA

ELASTANE
High Chlorine
resistance

OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
21CX00135 CENTROCOT


Tested for harmful substances.
www.oeko-tex.com/standard100

WORK IN ECO

Global Recycled Standard

creora
highcolor

WEIGHT (±5%)		WIDTH (+3%/-2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
205 g/m ²	308 g/m lin.	150 cm	41/cm	26/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL <small>AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)</small>	max -5% WIDTH	max -5% LENGTH
RESISTANCE TO PILLING <small>ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD</small>	4 to 4.5	
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) <small>AATCC 183-2010</small>	40/50+	
STRETCH TO DYNAMOMETER (±15%) <small>ASTM D4964 - LOAD 20 Lbs</small>	85% WIDTH <small>(min 72% - max 98%)</small>	120% LENGTH <small>(min 102% - max 138%)</small>
MODULUS @ % ELONGATION (30% - 50% - 70%)	30% 50% 70%	30% 50% 70%
	0.9 - 1.8 2.5 - 4.5 6.3 - 12.0	0.5 - 1.0 1.5 - 3.0 3.0 - 5.5
	WIDTH Lbs	WIDTH Lbs
CARE LABELLING CODES		

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.