


TECHNICAL DATA SHEET

28/12/2021

N110
KIRA
PRINTED

COMPOSITION



NYLON








ELASTANE
High Chlorine
resistance



UPF 50+



WEIGHT (±5%)		WIDTH (+/-2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
195 g/m ²	296 g/m lin.	150 cm	46/cm	26/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	max -5% WIDTH		max -5% WIDTH			
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	4 to 4.5					
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) AATCC 183-2010	50+					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs	110% WIDTH (min 94% - max 127%)		205% LENGTH (min 174% - max 236%)			
MODULUS @ % ELONGATION (30% - 50% - 70%)	30%	50%	70%	30%	50%	70%
	0.3 - 0.9	0.9 - 1.9	2.0 - 3.8	0.0 - 0.2	0.2 - 0.9	0.9 - 1.5
	WIDTH Lbs			WIDTH Lbs		
CARE LABELLING CODES	    					

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.