

TECHNICAL DATA SHEET

15/06/2020

N130

SHIRA

PRINTED

COMPOSITION

80%
PA

TRILOBATE
NYLON


20%
EA

ELASTANE
High Chlorine
resistance






WEIGHT (±5%)		WIDTH (+/-2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
190 g/m ²	285 g/m lin.	148 cm	46/cm	26/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL <small>AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)</small>	max -5% WIDTH	max -5% LENGTH
RESISTANCE TO PILLING <small>ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD</small>	4 to 4.5	
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) <small>AATCC 183-2010</small>	50+	
STRETCH TO DYNAMOMETER (±15%) <small>ASTM D4964 - LOAD 20 Lbs</small>	115% WIDTH <small>(min 98% - max 132%)</small>	200% LENGTH <small>(min 170% - max 230%)</small>
MODULUS @ % ELONGATION (30% - 50% - 70%)	30% 50% 70%	30% 50% 70%
	0.2 - 0.8 0.8 - 1.6 1.7- 3.1	0.0- 0.3 0.3 - 0.9 0.9 - 1.6
	WIDTH Lbs	WIDTH Lbs
CARE LABELLING CODES		

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.