

TECHNICAL DATA SHEET


28/12/2021

N210


KARIMA

PRINTED





COMPOSITION




80%
PA
NYLON



20%
EA
ELASTANE
High Chlorine
resistance

| WEIGHT (±5%) | | WIDTH (+/-2%) | COURSES | WALES | TOLERANCE FOR COMPOSITION (STANDARD ASTM) |
|----------------------|--------------|---------------|---------|-------|---|
| 175 g/m ² | 266 g/m lin. | 150 cm | 41/cm | 25/cm | ±3% |

| | | |
|--|--|---|
| DIMENSIONAL CHANGE OF FABRIC AFTER HL <small>AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)</small> | max -5% WIDTH | max -5% LENGTH |
| RESISTANCE TO PILLING <small>ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD</small> | 4 to 4.5 | |
| ULTRAVIOLET PROTECTION FACTOR (U.P. F.) <small>AATCC 183-2010</small> | 50+ | |
| STRETCH TO DYNAMOMETER (±15%) <small>ASTM D4964 - LOAD 20 Lbs</small> | 115% WIDTH <small>(min 98% - max 132%)</small> | 180% LENGTH <small>(min 153% - max 207%)</small> |
| MODULUS @ % ELONGATION (30% - 50% - 70%) | 30% 50% 70% | 30% 50% 70% |
| | 0.2 - 0.7 0.7 - 1.6 1.6 - 3.1 | 0.0 - 0.3 0.4 - 1.0 1.0 - 1.8 |
| CARE LABELLING CODES |  | |

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.