

TECHNICAL DATA SHEET

28/12/2021

N610 JUSTIN PRINTED

COMPOSITION

77%
PA


NYLON

23%
EA

ELASTANE
High Chlorine
resistance



WEIGHT (±5%)		WIDTH (+/-2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
155 g/m ²	220 g/m lin.	140 cm	45/cm	26/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	max -5% WIDTH			max -5% LENGTH		
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	4 to 4.5					
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) AATCC 183-2010	40/50+					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs	210% WIDTH (min 179% - max 242%)			130% LENGTH (min 111% - max 150%)		
MODULUS @ % ELONGATION (30% - 50% - 70%)	30%	50%	70%	30%	50%	70%
	0.0 - 0.3	0.3 - 0.8	0.8 - 1.4	0.4 - 1.0	1.0 - 1.8	1.8 - 3.0
	WIDTH Lbs			WIDTH Lbs		
CARE LABELLING CODES						

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.