

TECHNICAL DATA SHEET

28/12/2021

N710
LEO
PRINTED

COMPOSITION

81%
PA

TEXTURIZED
NYLON

19%
EA


ELASTANE
High Chlorine
resistance



UPF 50+



WEIGHT (±5%)		WIDTH (+/-2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
210 g/m ²	320 g/m lin.	150 cm	40/cm	24/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	max -5% WIDTH		max -5% LENGTH			
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	4 to 4.5					
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) AATCC 183-2010	50+					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs	150% WIDTH (min 128% - max 173%)		90% LENGTH (min 77% - max 104%)			
MODULUS @ % ELONGATION (30% - 50% - 70%)	30%	50%	70%	30%	50%	70%
	0.2 - 0.8	0.8 - 1.8	1.8 - 3.2	0.9 - 1.7	1.7 - 4.2	5.0 - 10.0
	WIDTH Lbs			WIDTH Lbs		
CARE LABELLING CODES						

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.