


TECHNICAL DATA SHEET PROVISIONAL

26/02/2022

N813


CLOUD REC PRINTED

COMPOSITION







87%
PA REC

RECYCLED
NYLON








13%
EA

ELASTANE
High Chlorine
resistance

WEIGHT (±5%)		WIDTH (+/-2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
140 g/m ²	210 g/m lin.	148 cm	38/cm	28/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	max -5% WIDTH			max -5% LENGTH		
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	4 to 4.5					
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) AATCC 183-2010	40/50+					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs	125% WIDTH (min 106% - max 144%)			120% LENGTH (min 102% - max 138%)		
MODULUS @ % ELONGATION (30% - 50% - 70%)	30%	50%	70%	30%	50%	70%
	0.0 - 0.3	0.3 - 1.0	1.0 - 2.4	0.1 - 0.6	0.6 - 1.3	1.3 - 2.2
	WIDTH Lbs			WIDTH Lbs		
CARE LABELLING CODES	    					

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.