

N840 BAHIA REC

EFFORTLESS STYLE

APPLICATIONS & TECHNICAL DATA

WORK TO PLAY
JOGGERS



TENNIS / GOLF
OUTFITS



BOARDSHORTS



COMPOSITION (ASTM STANDARD ±3% TOLERANCE)

75%
DTY RECYCLED
NYLON

25%
ELASTANE
HIGH-CHLORINE RESISTANCE

WEIGHT
(±5% TOLERANCE)

WIDTH
(+3% / -2% TOLERANCE)

160 G/M²

144 CM

4.7 OZ/YD²

56.7 INCHES

COURSES

WALES

50 / CM

25 / CM

127 / INCHES

64 / INCHES

DIMENSIONAL CHANGE OF FABRIC AFTER HL
AATCC 135-2015 (1 WASH, NORMAL CYCLE AT 41
DEGREE CELSIUS LINE DRY)

MAX -5%
WIDTH

MAX -5%
LENGHT

RESISTANCE TO PILLING
ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES
PHOTOGRAPHIC RATING STD

4.0 TO 4.5

ULTRAVIOLET PROTECTION FACTOR (U.P.F.)
AATCC 183-2010

50+

SOLID FABRIC

STRETCH TO DYNAMOMETER (±15%)
ASTM D4964 - LOAD 20 LBS

155%

WIDTH
(MIN 132% - MAX 178%)

120%

LENGTH
(MIN 102% - MAX 138%)

MODULUS @ % ELONGATION (30% - 50% - 70%)

30%	50%	70%	30%	50%	70%
0.4 - 0.9	1.0 - 1.2	2.2 - 4.0	0.1 - 0.6	0.6 - 1.2	1.2 - 2.0

CARE LABELLING SYMBOLS




2616 WASHED NAVY



4718 COCOA POWDER



0919 NERO



0210 WHITE SOLID / 0120 WHITE PFF