

# TECHNICAL DATA SHEET PROVISIONAL

31/03/2023

**N840**  
**BAHIA**  
**SOLID**

## COMPOSITION



RECYCLED  
NYLON








ELASTANE  
High Chlorine  
resistance



UPF 50+

WEIGHT (±5%)		WIDTH (+3%/ -2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
160 g/m <sup>2</sup>	230 g/m lin.	144 cm	50/cm	25/cm	±3%

<b>DIMENSIONAL CHANGE OF FABRIC AFTER HL</b> AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	max -5% WIDTH		max -5% LENGTH			
<b>RESISTANCE TO PILLING</b> ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	4 to 4.5					
<b>ULTRAVIOLET PROTECTION FACTOR (U.P. F.)</b> AATCC 183-2010	50+					
<b>STRETCH TO DYNAMOMETER (±15%)</b> ASTM D4964 - LOAD 20 Lbs	145% WIDTH (min 123% - max 167%)		115% LENGTH (min 98% - max 132%)			
<b>MODULUS @ % ELONGATION (30% - 50% - 70%)</b>	30%	50%	70%	30%	50%	70%
	0.4 - 0.5	0.9 - 1.2	1.6 - 1.9	0.5 - 0.8	1.5 - 1.9	3.1 - 3.7
	WIDTH Lbs			LENGTH Lbs		
<b>CARE LABELLING CODES</b>	    					

## SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.