

TECHNICAL DATA SHEET **PROVISIONAL**

22/12/2023

N850 FISHTALE PRINTED

COMPOSITION



80%
PA REC

RECYCLED
NYLON



20%
EA REC

RECYCLED
ELASTANE
Chlorine
resistant




OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
21CX00135 CENTROCOT
Tested for harmful substances.
www.oeko-tex.com/standard100






WEIGHT (±5%)		WIDTH (+3%/-2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
200 g/m²	292 g/m lin.	143 cm	53/cm	25/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL <small>AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)</small>	max -5% WIDTH	max -5% LENGTH												
RESISTANCE TO PILLING <small>ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD</small>	4-5													
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) <small>AATCC 183-2010</small>	50+													
STRETCH TO DYNAMOMETER (±15%) <small>ASTM D4964 - LOAD 20 Lbs</small>	95% WIDTH <small>(min 81% - max 109%)</small>	170% LENGTH <small>(min 145% - max 195%)</small>												
MODULUS @ % ELONGATION (30% - 50% - 70%)	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 33%; text-align: center;">30%</td> <td style="width: 33%; text-align: center;">50%</td> <td style="width: 33%; text-align: center;">70%</td> </tr> <tr> <td style="text-align: center;">0.5 - 0.8</td> <td style="text-align: center;">1.5 - 1.9</td> <td style="text-align: center;">3.9 - 5.0</td> </tr> </table>	30%	50%	70%	0.5 - 0.8	1.5 - 1.9	3.9 - 5.0	<table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 33%; text-align: center;">30%</td> <td style="width: 33%; text-align: center;">50%</td> <td style="width: 33%; text-align: center;">70%</td> </tr> <tr> <td style="text-align: center;">0.2 - 0.3</td> <td style="text-align: center;">0.9 - 1.1</td> <td style="text-align: center;">1.6 - 1.8</td> </tr> </table>	30%	50%	70%	0.2 - 0.3	0.9 - 1.1	1.6 - 1.8
	30%	50%	70%											
0.5 - 0.8	1.5 - 1.9	3.9 - 5.0												
30%	50%	70%												
0.2 - 0.3	0.9 - 1.1	1.6 - 1.8												
WIDTH Lbs		LENGTH Lbs												
CARE LABELLING CODES														

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.