

N212 SAND REC PRINTED



TECHNICAL DATASHEET 12/05/2025

COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES
80% RECYCLED NYLON	20% ELASTANE HIGH-CHLORINE RESISTANCE	175 g/m ²	148 cm	45 / cm	26 / cm
		5.2 oz/ld ²	58 inches	114 / inch	66 / inch
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low)			max -5% WIDTH		max -5% LENGTH
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			4.0 to 4.5		
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			50+		
PRINTED					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs			115% WIDTH (min 98% - max 132%)		180% LENGTH (min 153% - max 207%)
MODULUS @ % ELONGATION (30%-50%-70%)			30%	50%	70%
			0.2 - 0.7	0.7 - 1.7	1.7-3.5
			WIDTH Lbs		LENGTH Lbs
CARE LABELLING CODES					

CERTIFICATIONS



UPF 50+

FUNCTIONAL YARNS



SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.