

N212 SAND REC SOLID + PFP



TECHNICAL DATASHEET 25/03/2025

COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3% / -2% TOLERANCE)	COURSES	WALES							
80% RECYCLED NYLON	20% ELASTANE HIGH-CHLORINE RESISTANCE	175 g/m ²	150 cm	45 / cm	26 / cm							
		5.2 oz/yd ²	59 inches	114 / inch	66 / inch							
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low)			max -5% WIDTH		max -5% LENGTH							
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			4.0 to 4.5									
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			50+									
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs				SOLID			PFP					
				115% WIDTH (min 98% - max 132%)		185% LENGTH (min 157% - max 213%)		105% WIDTH (min 89% - max 121%)		170% LENGTH (min 145% - max 196%)		
MODULUS @ % ELONGATION (30%- 50%- 70%)				30%	50%	70%	30%	50%	70%	30%	50%	70%
				0.2 - 0.7	0.7 - 1.5	1.5 - 2.9	0.1 - 0.4	0.4 - 1.1	1.1 - 1.8	0.3 - 0.9	0.9 - 2.0	2.0 - 4.2
CARE LABELLING CODES												

CERTIFICATIONS



CU1004128GRS-2023-00035481



21CX00135
CENTROCOT



UPF 50+

FUNCTIONAL YARNS



SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.