

# N230 SHIRA LIGHT PRINTED

TECHNICAL DATASHEET 26/03/2025



COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES			
80% TRILOBAL NYLON	20% ELASTANE HIGH-CHLORINE RESISTANCE	170 g/m <sup>2</sup>	148 cm	44 / cm	26 / cm			
		5.0 oz/ld <sup>2</sup>	58 inches	112 / inch	66 / inch			
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low)			max -5% WIDTH		max -5% LENGTH			
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			4.0 to 4.5					
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			50+					
<b>PRINTED</b>								
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs			130% WIDTH (min 111% - max 150%)		190% LENGTH (min 162% - max 219%)			
MODULUS @ % ELONGATION (30%-50%-70%)			30%	50%	70%	30%	50%	70%
			0.1 - 0.7	0.7 - 1.3	1.4 - 2.4	0.0 - 0.5	0.5 - 1.1	1.1 - 1.7
			WIDTH Lbs			LENGTH Lbs		
CARE LABELLING CODES								

## CERTIFICATIONS



UPF 50+

## FUNCTIONAL YARNS

**CREORA**  
Highclo

**SPECIAL RECOMMENDATIONS:** WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.