

N813 CLOUD REC SOLID + PFP

TECHNICAL DATASHEET 25/03/2025



COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3% / -2% TOLERANCE)			COURSES	WALES							
87% RECYCLED NYLON	13% ELASTANE HIGH-CHLORINE RESISTANCE	140 g/m ²	150 cm			42 / cm	28 / cm							
		4.1 oz/yd ²	59 inches			107 / inch	71 / inch							
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low)			max -5% WIDTH			max -5% LENGTH								
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			4.0 to 4.5											
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			40/50+											
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs			SOLID			PFP								
			125% WIDTH (min 106% - max 144%)			130% LENGTH (min 110% - max 149%)			115% WIDTH (min 98% - max 132%)			130% LENGTH (min 110% - max 149%)		
MODULUS @ % ELONGATION (30%- 50%- 70%)			30%	50%	70%	30%	50%	70%	30%	50%	70%	30%	50%	70%
			0.0 - 0.3	0.3 - 0.7	0.7 - 1.9	0.1 - 0.5	0.5 - 1.0	1.0 - 2.0	0.0 - 0.4	0.4 - 1.2	1.2 - 2.4	0.1 - 0.6	0.6 - 1.2	1.2 - 2.2
CARE LABELLING CODES														

CERTIFICATIONS



SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.