

# N818 PALM REC PRINTED



TECHNICAL DATASHEET 25/03/2025

COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES			
80% RECYCLED NYLON	20% ELASTANE HIGH-CHLORINE RESISTANCE	180 g/m <sup>2</sup>	147 cm	47 / cm	28 / cm			
		5.3 oz/yd <sup>2</sup>	58 inches	119 / inch	71 / inch			
<b>DIMENSIONAL CHANGE OF FABRIC AFTER HL</b> AATCC 135 (1 wash, normal cycle at 41 degree Celsius, tumble dry low)			<b>max -5%</b> WIDTH		<b>max -5%</b> LENGTH			
<b>RESISTANCE TO PILLING</b> ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			<b>4.0 to 4.5</b>					
<b>ULTRAVIOLET PROTECTION FACTOR (U.P.F.)</b> AATCC 183			<b>50+</b>					
<b>PRINTED</b>								
<b>STRETCH TO DYNAMOMETER (±15%)</b> ASTM D4964 - LOAD 20 Lbs			<b>105%</b> WIDTH (min 89% - max 121%)		<b>160%</b> LENGTH (min 136% - max 184%)			
<b>MODULUS @ % ELONGATION (30%-50%-70%)</b>			30%	50%	70%	30%	50%	70%
			<b>0.1 – 0.7</b>	<b>0.7 – 1.7</b>	<b>1.7 – 4.2</b>	<b>0.2 - 0.7</b>	<b>0.7 – 1.5</b>	<b>1.4 – 2.1</b>
			<b>WIDTH Lbs</b>			<b>LENGTH Lbs</b>		
<b>CARE LABELLING CODES</b>								

## CERTIFICATIONS



UPF 50+

## FUNCTIONAL YARNS



**SPECIAL RECOMMENDATIONS:** WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.