

# N840 BAHIA REC SOLID

TECHNICAL DATASHEET 25/03/2025



COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES
75% RECYCLED NYLON	25% ELASTANE HIGH-CHLORINE RESISTANCE	160 g/m <sup>2</sup>	144 cm	50 / cm	25 / cm
		4.7 oz/ld <sup>2</sup>	56.7 inches	127 / inch	64 / inch
<b>DIMENSIONAL CHANGE OF FABRIC AFTER HL</b> AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low)			<b>max -5%</b> WIDTH		<b>max -5%</b> LENGTH
<b>RESISTANCE TO PILLING</b> ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			<b>4.0 to 4.5</b>		
<b>ULTRAVIOLET PROTECTION FACTOR (U.P.F.)</b> AATCC 183			<b>50+</b>		
<b>SOLID</b>					
<b>STRETCH TO DYNAMOMETER (±15%)</b> ASTM D4964 - LOAD 20 Lbs			<b>155%</b> WIDTH (min 132% - max 178%)		<b>120%</b> LENGTH (min 102% - max 138%)
<b>MODULUS @ % ELONGATION (30%-50%-70%)</b>			30%	50%	70%
			0.4 - 0.9	1.0-1.2	2.2-4.0
			<b>WIDTH Lbs</b>		<b>LENGTH Lbs</b>
<b>CARE LABELLING CODES</b>					

## CERTIFICATIONS



CU1004128GRS-2023-00035481



STANDARD 100

21CX00195

CENTROCOT



UPF 50+

## FUNCTIONAL YARNS

**CREORA**  
Highclo

**SPECIAL RECOMMENDATIONS:** WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.