

N850 FISHTALE SOLID

TECHNICAL DATASHEET August 2026



COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES			
80% RECYCLED NYLON	20% RECYCLED ELASTANE HIGH-CHLORINE RESISTANCE	200 g/m²	146 cm	51/ cm	28/ cm			
		5.9 oz/yd²	57.5 inches	130/ inch	71/ inch			
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low) RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			max -5% WIDTH		max -5% LENGTH			
			4.5					
			50+					
SOLID								
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs MODULUS @ % ELONGATION (30%-50%-70%) CARE LABELLING CODES			95% WIDTH (min 81% - max 109%)		170% LENGTH (min 145% - max 196%)			
			30%	50%	70%	30%	50%	70%
			0.5 – 0.8	1.5 – 1.9	3.9 – 5.0	0.2 - 0.3	0.9 – 1.1	1.6 - 1.8
			WIDTH Lbs			LENGTH Lbs		

CERTIFICATIONS



FUNCTIONAL YARNS



SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product’s quality, we reserve the right to modify these data while necessary.

Update: removed highclo logo.

Replaces the previous data sheet of March 2025.