

P365 ATLANTIS REC SOLID + PFP



TECHNICAL DATASHEET July 2026

COMPOSITION (ASTM STANDARD ±3% TOLERANCE)			WEIGHT (±5% TOLERANCE)			WIDTH (+3% / -2% TOLERANCE)			COURSES			WALES			
78% RECYCLED POLYESTER DTY	22% ELASTOLEFIN* CHLORINE - PROOF	190 g/m²	150 cm			34 / cm			27 / cm						
		5.6 oz/yd²	59 inches			86 / inch			69 / inch						
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low)				max -5% WIDTH						max -5% LENGTH					
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD				4.0 to 4.5											
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183				50+											
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs MODULUS @ % ELONGATION (30%- 50%- 70%)				SOLID						PFP					
				145% WIDTH (min 123% - max 167%)			140% LENGTH (min 119% - max 161%)			130% WIDTH (min 111% - max 150%)			130% LENGTH (min 111% - max 150%)		
				30%	50%	70%	30%	50%	70%	30%	50%	70%	30%	50%	70%
				0.0 – 0.2	0.4 – 1.0	1.1 – 2.3	0.3 - 0.8	1.0 – 2.1	2.1 – 3.7	0.0 – 0.2	0.6 – 1.2	1.5 – 2.8	0.3 - 0.7	1.3 – 2.4	2.4 – 4.4
CARE LABELLING CODES															

CERTIFICATIONS



CU1004128GRS-2023-00035481

STANDARD 100

21CK00135

CENTROCOT



UPF 50+

FUNCTIONAL YARNS



REPREVE

SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.

* Elastolefin **XLANCE**®

Update: Composition description revised to "Chlorine - Proof" instead of "Chlorine - High Resistance".

Replaces the previous data sheet of June 2026.