



SPORTSWEAR

CONNECTING SUSTAINABLE SOLUTIONS WITH PERFECT FITTING. FOX REC OFFERS SOFT FEELING, SUPERIOR ELASTICITY, POWER AND DRY-COMFORT. MADE WITH 100% RECYCLED POLYESTER IS THE SUSTAINABLE CHOICE FOR HIGH-PERFORMANCE LEGGINGS, YOGA-WEAR AND SPORTS BRAS THAT SHAPES THE BODY KEEPING IT DRY, THANKS TO ITS QUICK-DRY EMBEDDED PROPERTY.




P740 FOX REC

COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)		WIDTH (+3% / -2% TOLERANCE)		COURSES		WALES				
84% DTY RECYCLED POLYESTER	16% ELASTANE HIGH-CHLORINE RESISTANCE	215 G/M ²		153 CM		41 / CM		28 / CM				
		6.3 OZ/YD ²		60 INCHES		104 / INCHES		71 / INCHES				
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 WASH, NORMAL CYCLE AT 41 DEGREE CELSIUS LINE DRY)				RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD				ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183-2010				
MAX -5% WIDTH		MAX -5% LENGTH		4.0 TO 4.5				50+				
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 LBS				SOLID		PFP						
135% WIDTH (MIN 115% - MAX 155%)				170% LENGTH (MIN 145% - MAX 196%)		105% WIDTH (MIN 89% - MAX 121%)		140% LENGTH (MIN 119% - MAX 161%)				
MODULUS @ % ELONGATION (30% - 50% - 70%)				30%	50%	70%	30%	50%	70%			
0.1 - 0.7 0.6 - 1.5 1.5 - 3.2				0.1 - 0.5	0.8 - 1.6	1.5 - 2.5	0.3 - 1.0	1.2 - 2.6	3.0 - 5.6			
0.0 - 0.5 0.9 - 2.1 2.2 - 3.8				0.0 - 0.5	0.0 - 0.5	0.0 - 0.5	0.0 - 0.5	0.0 - 0.5	0.0 - 0.5			
CARE LABELLING SYMBOLS												



*2413 NEON PINK



10717 DEEP TEAL



6619 BLACK



3310 WHITE / 3710 PFP

AATCC STANDARDS

COLOUR	CHLORINATED WATER AATCC 162	LIGHT AATCC 16-20 AFU				WATER 38°C AATCC 107				SEA WATER 38°C AATCC 106				PERSPIRATION AATCC 15				CROCKING AATCC 8		WASHING 49°C AATCC 61-2A							
	C.C.	C.C.	C.C.	AC	CO	PA	PL	PC	WO	C.C.	AC	CO	PA	PL	PC	WO	S.CO DRY	S.CO WET	C.C.	AC	PA	PL	PC	WO			
3310 / 3710	4	4	4.5	5	5	5	5	5	5	4.5	5	5	5	5	5	4.5	5	5	5	5	5	5	4.5	5	5	5	
*2413	4	3-10AFU	4.5	4	4.5	4	4.5	4.5	4.5	4.5	4	4.5	4	4.5	4.5	4.5	4.5	4.5	4.5	4	4.5	3	4	2.5	4	4.5	
10717	4.5	4	4.5	3.5	4	3.5	4	4.5	4	4.5	3.5	4	3.5	4	4.5	4	4.5	4	4.5	4	4	4.5	3	3.5	4.5	4	
6619	4.5	4.5	4.5	3.5	4	3	3.5	4.5	3.5	4.5	4	3	3.5	4	3.5	4.5	4	4.5	4.5	4	3	3	4.5	3.5	4	3.5	4

* FLUORESCENT COLOURS

* FLUORESCENT COLOURS - CF TO LIGHT AATCC 16-10 AFU

ISO STANDARDS

COLOUR	CHLORINATED WATER ISO 105-E03	LIGHT ISO 105-B02				WATER ISO 105-E01				SEA WATER ISO 105-E02				ALKALINE PERSPIRATION PH 8.0 ISO 105-E04				ACID PERSPIRATION PH 5.5 ISO 105-E04				CROCKING ISO 105-X12		WASHING 40°C ISO 105-C06 A25			
	C.C.	C.C.	C.C.	CO	PA	PL	C.C.	CO	PA	PL	C.C.	CO	PA	PL	C.C.	CO	PA	PL	S.CO DRY	S.CO WET	C.C.	CO	PA	PL			
3310 / 3710	3	4	4.5	5	5	5	4.5	5	5	5	4.5	5	5	5	4.5	5	5	5	5	5	4.5	5	5	5	4.5	5	
*2413	4	2-3	4.5	4.5	4	4.5	4.5	4.5	4	4.5	4.5	4	4.5	4.5	4.5	4.5	4.5	4.5	4	4.5	4	4.5	4	4.5	3	4.5	
10717	4	4	4.5	4.5	4	4.5	4.5	4.5	4	4.5	4.5	4	4.5	4.5	4.5	4.5	4.5	4.5	4	4	4	4.5	4	4.5	3	4.5	
6619	4.5	4.5	4.5	4	3.5	3.5	4.5	4	3.5	4	3.5	4	3.5	4	3.5	4.5	4	3.5	3	3	4.5	4	3.5	4	3.5	3	4.5

AVAILABLE COLORS THE 4 COLORS PRESENTED IN THIS PAGE ARE ALWAYS AVAILABLE FOR SAMPLING. IF YOU WOULD LIKE TO CHOOSE A COLOR FROM THE MAIN POLYESTER COLOR CARD, YOU CAN ENJOY A MCQ OF 70 MTS FOR BULK ORDERS. HOWEVER, THE RESULTING COLOR SHADE AND THE COLOR FASTNESS PERFORMANCES MAY BE SLIGHTLY DIFFERENT. WE WILL SUBMIT TO YOUR ATTENTION A LAB DIP SWATCH FOR APPROVAL BEFORE GOING ON WITH THE BULK PRODUCTION.

SPECIAL NOTES/WARNINGS WE RECOMMEND CARRYING OUT LAB TESTS FOR COLOR MATCHES, MOLDING, BONDING AND APPLICATIONS ON FABRICS IN ORDER TO PREVENT PROBLEMS FROM ARISING DURING GARMENTS PRODUCTION. PLEASE CAREFULLY CHECK PHYSICAL DATA AND COLOR FASTNESS FORECASTS.