

P740 FOX REC SOLID + PFP



TECHNICAL DATASHEET 12/05/2025

COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3% / -2% TOLERANCE)			COURSES	WALES							
84% RECYCLED POLYESTER DTY	16% ELASTANE HIGH-CHLORINE RESISTANCE	215 g/m ²	153 cm			41 / cm	28 / cm							
		6.3 oz/yd ²	60 inches			104 / inch	71 / inch							
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low)			max -5% WIDTH			max -5% LENGTH								
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			4.0 to 4.5											
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			50+											
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs			SOLID			PFP								
			135% WIDTH (min 115% - max 155%)			170% LENGTH (min 145% - max 196%)			105% WIDTH (min 89% - max 121%)			140% LENGTH (min 119% - max 161%)		
MODULUS @ % ELONGATION (30%- 50%- 70%)			30%	50%	70%	30%	50%	70%	30%	50%	70%	30%	50%	70%
			0.1 - 0.7	0.6-1.5	1.5-3.2	0.1-0.5	0.8-1.6	1.5-2.5	0.3 - 1.0	1.2 - 2.6	3.0 - 5.6	0.0 - 0.5	0.9 - 2.1	2.2 - 3.8
CARE LABELLING CODES														

CERTIFICATIONS



FUNCTIONAL YARNS



UPF 50+

SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.