

P527 DORY SOLID + PFP



PROVISIONAL TECHNICAL DATASHEET 24/03/2025

COMPOSITION (ASTM STANDARD ±3% TOLERANCE)			WEIGHT (±5% TOLERANCE)			WIDTH (+3% / -2% TOLERANCE)			COURSES			WALES			
84% RECYCLED POLYESTER	16% ELASTANE HIGH-CHLORINE RESISTANCE	210 g/m²	149 cm			44 / cm			26 / cm						
		6.2 oz/yd²										58.5 inches			112 / inch
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low)				max -5% WIDTH				max -5% LENGTH							
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD				4.0 to 4.5											
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183				50+											
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs MODULUS @ % ELONGATION (30%- 50%- 70%)				SOLID						PFP					
				115% WIDTH (min 98% - max 132%)			155% LENGTH (min 132% - max 178%)			95% WIDTH (min 81% - max 109%)			145% LENGTH (min 123% - max 167%)		
				30%	50%	70%	30%	50%	70%	30%	50%	70%	30%	50%	70%
				0.2-0.9	1.0-2.2	2.3-4.5	0-0.5	0.6-1.4	1.4-2.5	0.7-1.4	1.8-3.2	4.5-8.0	0.0-0.1	0.9-1.3	1.8-2.6
CARE LABELLING CODES															

CERTIFICATIONS



FUNCTIONAL YARNS

SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.