

N630 RIB 04 NYLON SOLID+ PFP



PROVISIONAL TECHNICAL DATASHEET December 2025



COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES
81% NYLON	19% ELASTANE HIGH-CHLORINE RESISTANCE	200 g/m ²	150 cm	45 / cm	26 / cm
		5.9 oz/yd ²	59 inches	114 / inch	66 / inch
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41 degree Celsius, tumble dry low)			max -5% WIDTH	max -5% LENGTH	
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			4.0 to 4.5		
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			40/50+		
SOLID + PFP					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs			110% WIDTH (min 94% - max 127%)	230% LENGTH (min 196% - max 265%)	
MODULUS @ % ELONGATION (30%-50%-70%)			30%	50%	70%
			0.2-0.8	0.8-1.4	1.5-2.5
			WIDTH Lbs		LENGTH Lbs
CARE LABELLING CODES					

CERTIFICATIONS



SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.