

# N840 BAHIA REC PRINTED

**HYUN**  
Hung Yen Knitting & Dyeing Co.Ltd

PROVISIONAL TECHNICAL DATASHEET January 2026



COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES
75% RECYCLED NYLON	25% ELASTANE HIGH-CHLORINE RESISTANCE	160 g/m <sup>2</sup>	142 cm	50 / cm	25 / cm
		4.7 oz/ld <sup>2</sup>	56 inches	127 / inch	64 / inch
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low)			max -5% WIDTH		max -5% LENGTH
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			4.0 to 4.5		
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			50+		
PRINTED					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs			150% WIDTH (min 128% - max 173%)		130% LENGTH (min 111% - max 150%)
MODULUS @ % ELONGATION (30%-50%-70%)			30%	50%	70%
			0.2-0.8	0.8-1.6	1.6 - 2.5
			WIDTH Lbs		LENGTH Lbs
CARE LABELLING CODES					

## CERTIFICATIONS



UPF 50+

## FUNCTIONAL YARNS

**CREORA**  
Highclo

**SPECIAL RECOMMENDATIONS:** WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.