

N890 MIAMI SOLID

PROVISIONAL TECHNICAL DATASHEET December 2025



COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES
69% RECYCLED NYLON	31% ELASTANE HIGH-CHLORINE RESISTANCE	175 g/m ²	149 cm	51 / cm	23 / cm
		5.2 oz/yd ²	58.7 inches	130 / inch	58 / inch
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41 degree Celsius, tumble dry low)			max -5% WIDTH		max -5% LENGTH
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			4.0 to 4.5		
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			50+		
SOLID					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs			135% WIDTH (min 115% - max 155%)		95% LENGTH (min 81% - max 109%)
MODULUS @ % ELONGATION (30%-50%-70%)			30%	50%	70%
			0.3-0.9	0.9-1.8	1.8-3.2
			WIDTH Lbs		LENGTH Lbs
CARE LABELLING CODES					

CERTIFICATIONS



FUNCTIONAL YARNS

SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.