

# P527 DORY PRINTED



PROVISIONAL TECHNICAL DATASHEET 25/06/2025

COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES
<b>84%</b> RECYCLED POLYESTER	<b>16%</b> ELASTANE HIGH-CHLORINE RESISTANCE	210 g/m <sup>2</sup>	147 cm	44 / cm	26 / cm
		6.2 oz/yd <sup>2</sup>	57.8 inches	112 / inch	66 / inch
<b>DIMENSIONAL CHANGE OF FABRIC AFTER HL</b> AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low)			<b>max -5%</b> WIDTH	<b>max -5%</b> LENGTH	
<b>RESISTANCE TO PILLING</b> ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			<b>4.0 to 4.5</b>		
<b>ULTRAVIOLET PROTECTION FACTOR (U.P.F.)</b> AATCC 183			<b>50+</b>		
<b>PRINTED</b>					
<b>STRETCH TO DYNAMOMETER (±15%)</b> ASTM D4964 - LOAD 20 Lbs			<b>95%</b> WIDTH (min 81% - max 109%)		<b>150%</b> LENGTH (min 128% - max 173%)
<b>MODULUS @ % ELONGATION (30%-50%-70%)</b>			30%	50%	70%
			<b>0.7-1.4</b>	<b>2.0-3.4</b>	<b>4.8-8.2</b>
			<b>WIDTH Lbs</b>		<b>LENGTH Lbs</b>
<b>CARE LABELLING CODES</b>					

## CERTIFICATIONS



UPF 50+

## FUNCTIONAL YARNS

**SPECIAL RECOMMENDATIONS:** WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.