

# P640 RIB 03 PL SOLID

PROVISIONAL TECHNICAL DATASHEET December 2025



COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES			
85% RECYCLED POLYESTER	15% ELASTANE HIGH-CHLORINE RESISTANCE	215 g/m <sup>2</sup>	150 cm	40 / cm	26 / cm			
		6.3 oz/yd <sup>2</sup>	59 inches	102 / inch	66 / inch			
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41 degree Celsius, tumble dry low)			max -5% WIDTH		max -5% LENGTH			
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			4.0 to 4.5					
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			50+					
<b>SOLID</b>								
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs			85% WIDTH (min 72% - max 98%)		180% LENGTH (min 153% - max 207%)			
MODULUS @ % ELONGATION (30%-50%-70%)			30%	50%	70%			
			0.3-0.9	1.5-2.6	6.0-10.0	0.0-0.4	0.4-1.2	1.2-1.9
			WIDTH Lbs			LENGTH Lbs		
CARE LABELLING CODES								

## CERTIFICATIONS



CU1004128GRS-2023-00035481



STANDARD 100

21CX00135

CENTROCOT



UPF 50+

CREORA  
Highclo

**SPECIAL RECOMMENDATIONS:** WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.