

P650 RIB 04 PL SOLID



PROVISIONAL TECHNICAL DATASHEET December 2025



COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES
85% RECYCLED POLYESTER	15% ELASTANE HIGH-CHLORINE RESISTANCE	215 g/m ²	150 cm	40 / cm	26 / cm
		6.3 oz/yd ²	59 inches	102 / inch	66 / inch
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41 degree Celsius, tumble dry low)			max -5% WIDTH		max -5% LENGTH
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			4.0 to 4.5		
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			50+		
SOLID					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs			85% WIDTH (min 72% - max 98%)		175% LENGTH (min 149% - max 201%)
MODULUS @ % ELONGATION (30%-50%-70%)			30%	50%	70%
			0.3-0.9	1.6-2.8	6.5-10.8
			WIDTH Lbs		LENGTH Lbs
CARE LABELLING CODES					

CERTIFICATIONS



CU1004128GRS-2023-00035481



STANDARD 100

21CX00135
CENTROCOT



UPF 50+



SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.