

N960 ECOFIT BODY SOLID

PROVISIONAL TECHNICAL DATASHEET March 2026



COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES			
72% RECYCLED NYLON	28% ELASTANE HIGH-CHLORINE RESISTANCE	215 g/m ²	154 cm	48 / cm	28 / cm			
		6.3 oz/ld ²	60.5 inches	122 / inch	71 / inch			
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low)			max -5% WIDTH		max -5% LENGTH			
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			4 to 4.5					
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			50+					
SOLID								
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs			200% WIDTH (min 170% - max 230%)		115% LENGTH (min 98% - max 132%)			
MODULUS @ % ELONGATION (30%-50%-70%)			30%	50%	70%	30%	50%	70%
			0.1-0.5	0.5-1.1	1.1-1.6	0.7-1.5	1.8-3.3	3.3-6.0
			WIDTH Lbs			LENGTH Lbs		
CARE LABELLING CODES								

CERTIFICATIONS



CU1004128GRS-2023-00035481



STANDARD 100

21CX00135

CENTROCOT



UPF 50+

SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.