

P385 CIRCLE MAX SOLID

PROVISIONAL TECHNICAL DATASHEET 25/03/2025



| COMPOSITION (ASTM STANDARD ±3% TOLERANCE) | | WEIGHT (±5% TOLERANCE) | WIDTH (+3%/-2% TOLERANCE) | COURSES | WALES | | | |
|---|----------------------------------|---------------------------|---|-----------|---|-------------------|----------|-----|
| 57% RECYCLED POLYESTER | 43% RECYCLED POLYESTER PBT | 170 g/m ² | 155 cm | 26 / cm | 21 / cm | | | |
| | | 5.0 oz/yd ² | 61 inches | 66 / inch | 53 / inch | | | |
| DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low) | | | max -5% WIDTH | | max -5% LENGTH | | | |
| RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD | | | 4.0 to 4.5 | | | | | |
| ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183 | | | 40/50+ | | | | | |
| SOLID | | | | | | | | |
| STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs | | | 130% WIDTH (min 111% - max 150%) | | 65% LENGTH (min 55% - max 75%) | | | |
| MODULUS % ELONGATION (30%-50%-70%) | | | 30% | 50% | 70% | | | |
| | | | 0.0-0.4 | 0.4-1.2 | 1.2-2.5 | 1.2-2.6 | 5.0-10.0 | n/a |
| | | | WIDTH Lbs | | | LENGTH Lbs | | |
| CARE LABELLING CODES | | | | | | | | |

CERTIFICATIONS



CU1004128GRS-2023-00035481



STANDARD 100

21CX00135
CENTROCOT



SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.